



StyroGlue TF Base

A Non-cementitious, Tintable, Fiber-reinforced Base Coat



Coverage

Approximately 100ft² to 140ft² (9.3m² to 13.0m²). Coverage may vary due to ambient temperature, surface temperature, surface porosity, and/or application methods.

Packaging

65lb (29.48kg), 5 gallon (18.92L) pails

Storage

1. Store pails in a cool, dry location.
2. Store at a temperature between 40°F (4°C) and 90°F (32°C).
3. Store out of direct sunlight.
4. Protect pails from weather and other damage

Shelf Life

2 year

Color

Natural off-white color; may be colored using the Omega Color Bottle System

Product Description

StyroGlue TF Base is a 100% acrylic, water-based, fibered, non-cementitious base coat manufactured to be flexible and crack resistant. It eliminates the mixing and labor of working with portland cement base coats. The base coat can be tinted to the approximate color of the finish.

Features

Liquid Polymer

Excellent Workability

Water Resistant

Tintable

VOC Compliant

Benefits

Superior bond strength and flexibility

Easy and quick to apply

Increased resistance to moisture

Eliminates the need for primer

Less than 27 g/L

Basic Uses

StyroGlue TF Base is designed for use as a base coat in the AkroFlex EIF Systems and the AkroGold DEF System. It can be used as a skim coat over existing acrylic finishes.

NOTE: StyroGlue TF Base is not designed for use as an adhesive.

Area of Use

As a base coat over:

1. EPS foam board
2. Fiberglass mat-faced gypsum sheathing
3. EPS foam shapes

As a skim coat over:

1. Acrylic finishes

Surface Preparation

All surfaces to receive application must be clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents, and cleaning solutions. Ensure that all surfaces are smooth and free of any irregularities. Repair all cracks with the appropriate patching material for the existing substrate. Painted or glossy surfaces must be roughened to ensure a proper bond.

Mixing

1. See Omega Color Bottle System Data Sheet for color mixing instructions.
2. Mix thoroughly for approximately 3 to 5 minutes using a Jiffler-type mixer.

Application

See the appropriate AkroFlex EIFS ICC-ES Evaluation Report for additional application instructions and requirements.

For Use as a Base Coat

1. Apply the StyroGlue TF Base to the substrate a minimum of 1/16" (1.6mm) thick.
2. Completely embed AkroFlex Mesh into this coat.
3. Trowel smooth, ensuring that no mesh is visible.

For Use as a Skim Coat

1. Apply the material to the area needing to be leveled.
2. Application method will vary due to job conditions.

Drying

Drying time may vary due to climatic conditions, but should not take less than 24 hours at an ambient and surface temperature of 70°F (21°C) and 55% R.H. Variations in ambient and surface temperature and humidity may prolong drying time. All freshly applied material must be protected by an approved protective system from inclement weather until fully dry. It is the responsibility of the applicator to determine if the product is fully cured and/or dry prior to exposing it to rain, snow, dew, and/or any other inclement weather condition that may be detrimental to the product.

Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C). The ambient and surface temperature must stay consistently within this range until fully cured and/or dry (see DRYING). Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully cured and/or dry.

DO NOT add any other materials to the mixture of the product without written approval from Omega Products International, Inc.

DO NOT deviate in the mixing or application procedures contained in this, or any other Omega Product Data Sheets, without written approval from Omega Products International, Inc.

DO NOT apply StyroGlue TF Base if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and/or oils.

DO NOT use a Jiffler-type mixer that exceeds 500 RPM.

DO NOT leave StyroGlue Plus Base in its applied state.

DO NOT use as an adhesive.

NOTE: Failure to follow manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

Cleaning

Cleaning may be accomplished with water immediately after use.

Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN

www.omega-products.com

Disclaimer

Omega Products International, Inc. [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond

the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance

Technical assistance and information is available by calling Omega Products International, Inc. at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

Warranty

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.