



Coverage

Coarse, 16/20, and 20/30 -

Dash Finish: 8yd² to 10yd²
(6.7m² to 8.4m²)

Texture Finish: 10yd² to 16yd²
(8.4m² to 13.4m²)

Float Finish: 15yd² to 20yd²
(12.5m² to 16.7m²)

30/30 -

Float Finish (Scratch & Double):
8yd² to 10yd² (6.7m² to 8.4m²)

Coverage may vary due to ambient temperature, surface temperature, surface porosity, mixing methods, and/or application methods.

Packaging

Moisture resistive, 90lb (40.8kg) bags

Storage

1. Store bags in a cool, dry location.
2. Do not store in direct contact with the ground and/or concrete.
3. Store out of direct sunlight.
4. Protect bags from weather and other damage.

Shelf Life

1 year

Color

Premium Paint Grade grey in color; Paint Grade color varies

Product Description

ColorTek Paint Grade (PG) Exterior Stucco is a premium, factory blended, portland cement-based, stucco finish manufactured from the highest-grade portland cement, hydrated lime, graded aggregates, and specific additives. ColorTek PG comes in various aggregate combinations that allow design flexibility and a variety of finish textures. The following aggregate combinations are available, in order of aggregate size:

Coarse: Used to create heavy laced texture, sand finish, or machine dash finish

16/20: Used to create traditional texture, sand finish, or machine dash finish

20/30: Used to create a fine texture or sand finish

30/30: Used to create a uniform fine sand finish

ColorTek PG is designed to be painted and cannot be used with the ColorPak coloring system. It comes in the following grades:

- Premium Paint Grade
- Paint Grade

Features	Benefits
<i>Durable</i>	Long life-cycle with minimal maintenance
<i>Fire Resistant</i>	Does not burn
<i>Impact Resistant</i>	Resists impact damage
<i>Economical</i>	Lower cost product and easy to apply
<i>Insect Resistant</i>	Impervious to termites, rot, and fungus

Basic Uses

ColorTek PG is intended for use as a decorative, low-cost, low-maintenance finish.

Area of Use

ColorTek Paint Grade Exterior Stucco may be applied over the following products:

1. One coat stucco
2. Brown coat
3. Stucco
4. CMU/poured-in-place and/or tilt-up concrete/masonry
5. Approved Omega base coats and/or cementitious finishes

NOTE: When ColorTek is applied over polymer-modified base coats, the use of a bonding agent or acrylic admix is strongly recommended or may be required to ensure proper bond. See the applicable Omega system data sheet or base coat data sheet for additional information.



Sand 16/20



Sand 20/30



Sand 30/30

Optional Product Upgrades/Enhancements

PRODUCT	BENEFIT
E-FX Admix	Liquid admix to reduce efflorescence
AquaShield	Integral sealer to improve water-resistance, improve freeze/thaw performance, and reduce staining
AkroLoc/PolyLoc/Admix 500	Liquid admixtures that reduce cracking and increase tensile, bond, and flexural strengths
OmegaCure	Liquid accelerator to improve hydration, increase early strength/hardness, and allow cold weather application
Crack Isolation System	Supplementary system designed to mitigate surface cracking in new and existing plaster systems by integrating woven fiberglass mesh into the base coat or brown coat prior to applying the finish

Application Instructions



COLORTEK
PG EXTERIOR STUCCO

Surface Preparation

All surfaces to receive application must be clean and free of debris, dirt, dust, efflorescence, grease, oils, curing agents, and cleaning solutions. Ensure that all surfaces are smooth and free of any irregularities. Repair all cracks with the appropriate patching material for the existing substrate. Painted or glossy surfaces should be sandblasted to expose cementitious substrate and ensure a proper bond. The use of a bonder is recommended over cementitious substrates that are four or more months old. If a bonder is *not* used, just prior to application, dampen all surfaces that are to receive the ColorTek PG with clean, potable water.

Mixing

1. Add 3.25 gallons (12L) of clean, potable water per bag to an appropriate mixing apparatus.
2. Turn mixer on and add ColorTek PG bags to the water.
3. Allow the material to mix for a minimum of 15 minutes.
4. Turn mixer off and allow the material to take its initial set.
5. Retemper the material, adding only enough water to reach the desired consistency.
6. Do not over mix.

Application

ColorTek PG shall be applied to an approximate 1/8" thickness.

Hand Application Method

1. Using a hawk and trowel apply the material to the receiving surface, beginning at one corner and working to the next, in a single coat of uniform thickness.
2. Following the initial applicator, another person should texture or float the applied material to achieve the desired appearance.

Machine Sprayed Method

1. Add desired amount of mixed material to sprayer.
2. Begin spraying material onto the receiving surface, starting at a corner and not stopping until the opposite corner is reached. Avoid puddling.

Curing

Product should fully cure in 7 to 28 days following application. All freshly applied material must be protected by an approved protective system from inclement weather until fully dry. Curing time may vary due to ambient temperature, surface temperature, surface porosity, application methods, and/or thickness of material. It is the responsibility of the applicator to determine if the product is cured and/or dry prior to exposing it to rain, snow, dew, and/or any other inclement weather condition that may be detrimental to the product.

Limitations

DO NOT apply product when the ambient and surface temperature is below 40°F (4°C).^{*} When hot, dry, or windy conditions exist, moist curing and protection must be provided. The ambient and surface temperature must maintain the above requirements until fully cured (See CURING). Material that is allowed to freeze may suffer irreparable damage. Protect all work from inclement weather with an approved protective system until fully cured.

DO NOT add any other materials to the mixture of the product without written approval from Omega Products International, Inc.

DO NOT deviate in the mixing or application procedures contained in this, or any other Omega Product Data Sheets, without written approval from Omega Products International, Inc.

DO NOT apply ColorTek PG if there are contaminants on the receiving surface. Contaminates may include, but are not limited to, dust, debris, efflorescence, and/or oils.

DO NOT add any more water than prescribed.

DO NOT saturate the wall during preparation and/or wet curing.

DO NOT use excessive amounts of water when floating and/or troweling the texture.

NOTE: Failure to follow manufacturer's written specifications could result in the following, but not limited to spalling, cracking, peeling, chipping, delamination, discoloration, wash off, and overall system failure.

^{*} To ensure proper hydration in cold weather applications (approximately 50°F to 32°F) use OmegaCure admix. Refer to OmegaCure data sheet for additional information.

Cleaning

Cleaning may be accomplished with water immediately after use.

Safety

Avoid contact with eyes or prolonged contact with skin. Wash thoroughly after handling. In case of eye contact, flush immediately with running water for at least 15 minutes. Consult a physician immediately. Do not take internally. Be sure to provide adequate ventilation in enclosed areas. Use of an approved respirator is recommended.

KEEP OUT OF REACH OF CHILDREN



Heavy Lace



Heavy Dash

NOTE: More textures may be achieved using this product. Please see the ColorTek Color Chart for more information or contact Omega Products International.

www.omega-products.com

Disclaimer

Omega Products International, Inc. [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond

the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance

Technical assistance and information is available by calling Omega Products International, Inc. at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

Warranty

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.