



AquaShield

Water Repellant Admix for Stucco and Mortar



Packaging

1 lb (0.45kg) package

Storage

1. Store bags in a cool place, dry location
2. Do not store in direct contact with the ground and/or concrete
3. Store out of direct sunlight
4. Protect containers from weather and other damage.

Shelf Life

2 years

Color

White powder

Product Description

AquaShield is a powdered admixture designed to increase the water-resistance of ColorTek Stucco, mortar, or other approved cementitious products. AquaShield is added during mixing and offers the benefit of long-lasting water-resistance, improved stain resistance, and reduced efflorescence without the extra time and expense of applying a sealer.

Features

Benefits

Water-Resistant

Improved freeze/thaw resistance; less efflorescence and staining

Integral

Water-resistance throughout the thickness of the product, unlike surface sealers

Natural Appearance

Does not affect the color or appearance of the finish

Easy to Clean

Helps finish to resist dirt accumulation and allows for easy cleaning

Vapor Permeable

Allows wall to naturally breath which aids drying and helps to prevent mold

Easy to Use

Simply add during mixing; no additional sealers required

Basic Uses

AquaShield is designed as an admix to improve water repellent properties in ColorTek Stucco, mortar, and other cement-based products.

Area of Use

AquaShield may be added to the following products:

1. ColorTek Stucco
2. Mortar
3. Other approved cement-based products

Mixing

For use in ColorTek Stucco:

Refer to the appropriate ColorTek product data sheet for additional application and mixing information.

1. Add the mix water, ColorPak (if needed), and ColorTek to the mixer per the product data sheet(s).
2. After approximately 10 minutes of mixing the ColorTek, add a 1lb (0.45 kg) package of AquaShield into the mix per 90lb (40.8 kg) bag of ColorTek.
3. Allow the material to mix for a minimum of 5 additional minutes.
4. Turn mixer off and allow the material to take its initial set.
5. Retemper the material, adding only enough water to reach the desired consistency.
6. Do not over mix.

NOTE: If OmegaCoat is applied to stucco previously treated with Omega AquaShield then replace 1 gallon of the mixing water with 1 gallon of OmegaSeal 1000 (Penetrating Sealer) per 25-lb bag of OmegaCoat. Refer to the OmegaCoat product data sheet for additional application information.

For use in mortar:

Refer to the manufacturer's product data sheet and/or local code for additional application and mixing information.

1. Add the mix water and mortar to the mixer per manufacturer's and/or local code requirements.
2. After approximately 3 to 5 minutes of mixing, add a 1lb (0.45 kg) package of AquaShield into the mix per 94lb (42.6 kg) bag of mortar.
3. Allow the material to mix for a minimum of 5 additional minutes.
4. Turn mixer off and allow the material to take its initial set.
5. After approximately 5 to 10 minutes, break the set.

Contact Omega Products for use in other products.

Limitations

DO NOT apply at temperatures below 40°F (4°C) or above 90°F (32°C). Avoid freezing until the material is dry.

DO NOT use below grade.

DO NOT add any other material to the mixture of the product without written approval from Omega Products International, Inc.

DO NOT deviate in the mixing or application procedures contained in this, or any other Omega Products Data Sheets, without written approval from Omega Products International, Inc.

Cleaning

Cleaning may be accomplished with water and detergent immediately after use.

KEEP OUT OF REACH OF CHILDREN

www.omega-products.com

Disclaimer

Omega Products International, Inc. [Manufacturer] MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO THE PRODUCT(S) SOLD HEREIN. The recommendations, suggestions, statements and technical data are based on the best knowledge available to Manufacturer and are given for informational purposes ONLY and without any responsibility for their use. It is expressly understood and agreed, as a condition of the use of this product, that the buyer's sole and exclusive remedy for any claimed defective product against Manufacturer shall be the replacement of products actually proven to be defective. Handling and use of the products are beyond

the control of Manufacturer; therefore, no warranty is made, expressed or implied, as to the results obtained from the use of the product or against any claims for infringement of patents resulting from use of the product. Under no circumstance shall Manufacturer be liable for incidental or consequential damages arising out of the use or the improper application of the product. Before applying the product, the user shall determine the suitability of the product for his/her independent use, assuming all risks and liability whatsoever in connection therewith. This writing constitutes a complete and exclusive statement of the understanding between Manufacturer and Buyer.

Claims

Any Claimant shall notify Manufacturer immediately in writing of any alleged defect in the material. Claimant will provide Manufacturer with a reasonable and exclusive opportunity to investigate and test for the alleged defect. For any claim that is not valid Claimant agrees to pay Omega's reasonable charges, including travel and labor associated with investigation of such claim.

Technical Assistance

Technical assistance and information is available by calling Omega Products International, Inc. at (800) 600-6634 or FAX (951) 520-2594 or by e-mail at info@omega-products.com.

Warranty

The following is made in lieu of all expressed and implied rights, warranties and conditions, statutory or otherwise. The manufacturer's only obligation shall be to replace such quantity of products proven to be defective within one year following the date of manufacture, provided that the alleged defective product is returned prepaid to the manufacturer's plant and is accompanied with proof of purchase and batch number.